OKOUME-TWIN

REVISION 03 JUNE 2023

DESCRIPTION

Plywood panel made of outer faces rotary cut exotic "Okoume" (Aucouméa klaineana) with poplar inner layers. OKOUME-TWIN is available in a wide range of gluing and is particularly suitable for those applications who require good durability and high mechanical performances. Panguaneta exotic plywood meets the programs for forest sustainable development.

On demand OKOUME-TWIN can be supplied certified according to the FSC® (license Code FSC-C019345) and PEFC (PEFC/18-31-30) forest standard.

APPLICATIONS







BOATBUILDING

FURNITURE AND DESIGN

ARCHITECTURE AND CONSTRUCTION

CERTIFICATIONS









ON DEMAND ON DEMAND

FORMALDEHYDE RELEASE



GLUING













ON DEMAND

ON DEMAND

ON DEMAND

SIZES

	Standard	Unit	Value										
Standard sizes		mm		2500 x 1220 – 2500 x 1700 3100 x 1530 – 3100 x 1830									
Thickness	EN 315	mm	6	8	15	18	25	30	35	40			
Layers		nr.	5	5	7	9	11	13	15	17			

FEATURES

	Standard	Unit	Value		
Voluminal mass	EN 323	Kg/m ³	450 ± 10%		
Bending strength Long grain/Cross grain	EN 310	N/mm ²	from ≥34 / ≥23 for thickness 6 mm to ≥30 / ≥35 for thickness 40 mm		
Modulus of elasticity	EN 310	N/mm ²	≥3000 (average L/T)		
Thermal conductivity	EN 10456	W/m K	0,12		
Moisture	EN 322	%	8 ÷ 12		
Reaction to fire		1			
Standard	EN 13986		D-s2,d0 − Dfl-s1 (for thicknesses ≥9 mm and voluminal mass ≥400 kg/m³)		
On demand	EN 13501-1		Euroclasse B-s1,d0 (for thicknesses from 5 to 40 mm)		
Dimensional tolerances					
Thickness	EN 315	mm	+ (0,2 + 0,03 t); - (0,4 + 0,03 t)		
Length / Width	EN 315	mm	± 3,5		
Orthogonality	EN 315	mm/m	1		

None of the following tests has been subject to preliminary conditioning. The specific values are average values referred to the normal production. It is responsibility of the customer to determine if Panguaneta's products are suitable for the wished applications and to ensure that places and way of use comply with the supplier's instructions and with the law in force.